

COLLECTION: OOLONG

DESIGN: OXIDANT

BASIC INFORMATION

Brand	FR-One	Number of colour ways	12
Tariff item number	5515129000	MID	TRTEXTRABUR
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Double folded face in	Yes	Full roll diameter cm	22
Full roll diameter inch	8.66	Average piece length m	30
Minimum for special colour m	500	Delivery time weeks special lab dip	5
Railroaded	Yes		

CARE AND USAGE

Care code for washing °F

Washable at 140°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Maritime	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free

Yes

Prop 65

Yes

COLLECTION: **OOLONG**

DESIGN: **OXIDANT**

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	IMO FTPC part 7 drapery	Yes
Japanese L 1091	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 701 2010	Yes	NYNJ Port Authority - FAR 25.853 12 Pass	Yes
SN 198'898 Class 5.2	Yes	Italian UNI 9174 Classe Uno	Yes

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	7.11
Construction	9x7	Woven	Yes
Useable width cm	310	Useable width inch	122.05
Full width cm	312	Full width inch	122.83
Weight g/m ²	225	Thickness mm	0.520
Colouring type	Piece dyed	Filament or staple	32% Filament, 68% Staple
Textured or non textured	32% Textured, 68% Not Textured		

Type of finish

Sanforized	Yes	Thermofixed	Yes
------------	-----	-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: OOLONG

DESIGN: OXIDANT

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	5
------------------------------------	-----	--------------------------	---

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.14	Dimensional change weft	0.07
Dimensional change warp after ironing without steam	0.13	Dimensional change weft after ironing without steam	-0.13
Dimensional change warp after ironing with steam	-0.53	Dimensional change weft after ironing with steam	0.40

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-0.93	Dimensional change warp after ironing	-1.06
Dimensional change weft	-0.03	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.33	Dimensional change warp after ironing	-2.00
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.86	Dimensional change warp after ironing	-0.13
Dimensional change weft	0.03	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 D01	4-5		

COLLECTION: **OO LONG**

DESIGN: **OXIDANT**

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Is Textured	Yes	Warp Sizes	1048D
Warp Textured	Yes	Warp Threads per cm	9
Warp TPM	0		

Yarn 2

Weft Composition	100% Polyester inhene	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Is Textured	Yes	Weft Sizes	1162D
Weft Textured	Yes	Weft Threads per cm	7
Weft TPM	0		

DOWNLOADS / CERTIFICATES

Oxidant_American FMVSS 302	OxidantAmerican New York Port Authority FAR Part 25853 12 Second Vertical Test
Oxidant_Acoustic sound absorption measurement DRAPED	FROne_Sound absorption page
Oxidant_American Boston BFD IX1	Oxidant_American Hospital washing standard AATCC96
Oxidant_Italian UNI 9177 (Classe Uno)	Oxidant_International Maritime Organisation 2010 FTP Code Fire test procedures Part 7
Oxidant_British BS 5867 part 2 type B	Oxidant_AustralianNew Zealand AS 1530 part 2
OxidantGerman DIN 4102 B1	Oracle_AustralianNew Zealand AS 1530 part 3
Oxidant_Swiss SNV 198898	Oxidant_European EN 13773
Oxidant_British BS 5867 part 2 type C	Oxidant_Canadian CANULCS109
OxidantFrench NF P 92 503507 M1	Oxidant_American NFPA 701
Oxidant_American CAL 19	

