

COLLECTION: LAZARUS

DESIGN: LATIN

BASIC INFORMATION

Brand	FR-One	Number of colour ways	9
Tariff item number	5407530000	MID	TRTEXTRABUR
Country of origin	Türkiye	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	24
Full roll diameter inch	9.45	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care code comments also washable at 74°C /160F meeting American hospital washing standard AATCC96

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes	Maritime	Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free

Yes

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	IMO FTPC part 8 upholstery	Yes
IMO FTPC part 7 drapery	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 701 2010	Yes		

COLLECTION: LAZARUS

DESIGN: LATIN

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	17.78
Construction	33x31	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	360	Thickness mm	0.680
Colouring type	Yarn dyed	Filament or staple	92% Filament, 8% Staple
Textured or non textured	88.5% Textured, 11.5% Non-Textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Calender	Yes	Sanforized	Yes
Thermofixed	Yes	Washed	Yes

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: LAZARUS

DESIGN: LATIN

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Martindale rubs	50,000
Colour fastness to light	6	Wyzenbeek double rubs	50,000
Pilling	4	Brush pilling	4
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	50,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Acoustic absorption ISO 354 - ISO 11654	draped C/ flat D
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	200	Tearing strength weft N	210
-------------------------	-----	-------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	1800
-----------------------------	------	-----------------------------	------

Elongation - ISO 13934-1

Elongation warp %	25	Elongation weft %	26
-------------------	----	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

COLLECTION: LAZARUS

DESIGN: LATIN

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.19	Dimensional change warp after ironing	-1.19
Dimensional change weft	-0.89	Dimensional change weft after ironing	-0.99
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-1.83	Dimensional change warp after ironing	-1.99
Dimensional change weft	-1.59	Dimensional change weft after ironing	-1.53
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74° C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.23	Dimensional change warp after ironing	-1.06
Dimensional change weft	-0.93	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 D01	5		

COLLECTION: LAZARUS

DESIGN: LATIN

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester Inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	150 DEN	Warp Textured	Yes
Warp Threads per cm	24.75	Warp TPM	372

Yarn 2

Warp Composition	100% Polyester Inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	1433 DEN	Warp Textured	Yes
Warp Threads per cm	8.25	Warp TPM	NA

Yarn 3

Weft Composition	100% Polyester Inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	75 DEN	Weft Textured	Yes
Weft Threads per cm	7.75	Weft TPM	NA

Yarn 4

Weft Composition	100% Polyester Inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	150 DEN	Weft Textured	Yes
Weft Threads per cm	15.5	Weft TPM	375

Yarn 5

Weft Composition	100% Polyester Inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Is Textured	Yes	Weft Sizes	1666 DEN
Weft Textured	Yes	Weft Threads per cm	2.58
Weft TPM	NA		

Yarn 6

Weft Composition	100% Polyester Inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	1433 DEN	Weft Textured	Yes
Weft Threads per cm	5.17	Weft TPM	NA

COLLECTION: LAZARUS

DESIGN: LATIN

DOWNLOADS / CERTIFICATES

- | | |
|--|--|
|  <u>Latin_Australian_New Zealand AS 1530 part 2</u> |  <u>Latin_French NF P 92 503 507 M1</u> |
|  <u>Latin_American NFPA 260 UFAC</u> |  <u>Latin_American NFPA 701</u> |
| |  <u>Latin_American New York Port Authority FAR Part 25 853 12 Second</u> |
|  <u>FROne_Sound absorption page</u> |  <u>Vertical Test</u> |
|  <u>Latin_British BS7176 BS5852 crib 5</u> |  <u>Latin_Australian_New Zealand AS 1530 part 3</u> |
|  <u>Latin_American Boston BFD IX 1</u> |  <u>Latin_American CAL 19</u> |
| |  <u>Latin_International Maritime Organisation FTP Code Fire test procedures</u> |
|  <u>Latin_American CAL 117 SecE June 2013</u> |  <u>Part 7</u> |
|  <u>Latin_German DIN 4102 B1</u> |  <u>Latin_American Hospital washing standard AATCC96</u> |
|  <u>Latin_American FMVSS 302</u> |  <u>Latin_Swiss SNV 198898</u> |
|  <u>Latin_International Maritime Organisation 2010 FTP Code Fire test procedures Part 8</u> |  <u>Latin_European EN 1021</u> |
|  <u>Latin_Canadian CANULCS109</u> |  <u>Latin_European EN 13773</u> |
|  <u>Latin_British BS 5867 part 2 type B</u> |  <u>Latin_British BS 5867 part 2 type C</u> |

