

COLLECTION: MAY

DESIGN: BATISTE FR

BASIC INFORMATION

Brand	FR-One	Number of colour ways	9
Tariff item number	5407920000	MID	TRTEXTRABUR
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Double folded face in	Yes	Full width roll	Yes
Full roll diameter cm	21	Full roll diameter inch	8.27
Average piece length m	50	Minimum for special colour m	500
Delivery time weeks special lab dip		Railroaded	Yes

CARE AND USAGE

Care code comments	tumble dry low temperature	Care code for washing °F	Washable at 140°F gentle cycle
Type of finish	stenter+fixed		

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Maritime	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100

0611045
Centexbel

PFA-free

Yes

COLLECTION: MAY

DESIGN: BATISTE FR

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	Japanese L 1091	Yes
French NF P 92-503 507	M1	French NF P 92-504 507	M1
French NF P 92-505 507	M1	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	Taiwanese CNS10285-L31961	Yes
Italian UNI 9174 Classe Uno	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	74.29
Construction	30x22	Woven	Yes
Useable width cm	298	Useable width inch	117.32
Full width cm	300	Full width inch	118.11
Weight g/m ²	70	Thickness mm	0.000
Colouring type	Piece dyed	Zinc selvedge	Yes
Zinc selvedge weight g/m	22	Finish type	stenter+fixed

Type of finish

Washed	Yes
--------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: MAY

DESIGN: BATISTE FR

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	6
Acoustic absorption ISO 354 - ISO 11654	Draped E/ Flat E		

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	5
-------------------------	---

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	5
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	18	Tearing strength weft N	23
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	390	Tensile strength weft N/5cm	470
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	38.5	Elongation weft %	16
-------------------	------	-------------------	----

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.20	Dimensional change weft	0.10
Dimensional change warp after ironing without steam	0.00	Dimensional change weft after ironing without steam	0.20
Dimensional change warp after ironing with steam	-0.40	Dimensional change weft after ironing with steam	0.00

COLLECTION: MAY

DESIGN: BATISTE FR

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.50	Dimensional change warp after ironing	-0.80
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.70
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.33	Dimensional change warp after ironing	-1.79
Dimensional change weft	-0.27	Dimensional change weft after ironing	-0.27
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.20	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.20	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester Inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	70/24F
Warp Threads per cm	30	Warp TPM	800

Yarn 2

Weft Composition	100% Polyester Inherent	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	Ne 30/1
Weft Threads per cm	22	Weft TPM	NA

COLLECTION: MAY

DESIGN: BATISTE FR

DOWNLOADS / CERTIFICATES

- | | |
|---|--|
|  Batiste FR Canadian CAN ULC S109 |  Batiste FR British BS 5867 part 2 type B OLD |
|  Batiste FR American New York Port Authority FAR Part 25_853 12 Second Vertical Test |  Batiste FR International Maritime Organisation 2010 FTP Code Fire test procedures Part 7 |
|  Batiste FR Australian New Zealand AS 1530 part 2 |  Batiste FR Japanese JIS L1091 |
|  Batiste FR British BS 5867 part 2 type B |  Batiste FR American FMVSS 302 |
|  Batiste FR French NF P 92 503 507 M1 |  Batiste FR American Hospital washing standard AATCC96 |
|  Batiste FR European EN 13773 |  Batiste FR American NFPA 260 UFAC |
|  Batiste FR American CAL 117 SecE June 2013 |  Batiste FR American CAL 19 |
|  Batiste FR British BS 5867 part 2 type C |  Batiste FR American NFPA 701 |
|  Batiste FR German DIN 4102 B1 |  Batiste FR American Boston BFD IX 1 |
|  Batiste FR Australian New Zealand AS 1530 part 3 |  Batiste FR Kofeis1001 |

