

COLLECTION: **LOCI DIM OUT**

DESIGN: **LOCI DIM OUT**

BASIC INFORMATION

Brand	FR-One	Number of colour ways	24
Tariff item number	5407520000	MID	CNHANXIA88HAN
Country of origin	China	Characteristics	Dimout
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Double folded face in	Yes	Full roll diameter cm	23
Full roll diameter inch	9.06	Average piece length m	30
Minimum for special colour m	1000	Delivery time weeks special lab dip	2
Railroaded	Yes		

CARE AND USAGE

also washable at 74°C /160F meeting American hospital
Care code comments washing standard AATCC96

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Maritime	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



**STANDARD
100**
0611045
Centexbel

PFC-free	Yes	PFA-free	Yes
----------	-----	----------	-----

COLLECTION: **LOCI DIM OUT**

DESIGN: **LOCI DIM OUT**

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
American BFD IX 1	Yes	American CAL 19 section 1237.1	Yes
Canadian ULC S109 large flame	Yes	Canadian ULC S109 small flame	Yes
German B1 DIN 4102	Yes	European EN 13773	Yes
MVSS 302	Yes	IMO FTPC part 7 drapery	Yes
French NF P 92-503 507	M1	French NF P 92-504 507	M1
French NF P 92-505 507	M1	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	48.53
Construction	84x48	Woven	Yes
Useable width cm	300	Useable width inch	118.11
Full width cm	302	Full width inch	118.9
Weight g/m ²	272	Light transmission	92% spectrophotometer PE: lambda 900
Thickness mm	0.610	Colouring type	Piece dyed
Filament or staple	100% Filament	Textured or non textured	100% Textured

Treatment

No treatment	Yes
--------------	-----

Type of finish

Washed	Yes
--------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: **LOCI DIM OUT**

DESIGN: **LOCI DIM OUT**

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	5
Pilling	4-5	Brush pilling	4-5

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.02	Dimensional change weft	0.57
Dimensional change warp after ironing without steam	0.13	Dimensional change weft after ironing without steam	-0.40
Dimensional change warp after ironing with steam	-0.07	Dimensional change weft after ironing with steam	-0.13

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-0.60	Dimensional change warp after ironing	-0.53
Dimensional change weft	-0.13	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-1.56	Dimensional change warp after ironing	-1.46
Dimensional change weft	-0.73	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74° C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.86	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.53	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 D01	5		

COLLECTION: **LOCI DIM OUT**

DESIGN: **LOCI DIM OUT**

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	150D Pol+150D DTY HIM	Weft Textured	Yes
Weft Threads per cm	48	Weft TPM	NA

Yarn 2

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	150D Poly+150D HIM	Warp Textured	Yes
Warp Threads per cm	84	Warp TPM	NA

DOWNLOADS / CERTIFICATES

[Loci Dim Out International Maritime Organisation FTP Code Fire test](#)

[procedures Part 7](#)

[FROne Sound absorption page](#)

[Loci Dim Out Chinese GB 20286](#)

[Loci Dim Out AustralianNew Zealand AS 1530 part 2](#)

[Loci Dim Out Japanese JIS L1091](#)

[Loci Dim Out AustralianNew Zealand AS 1530 part 3](#)

[Loci Dim Out Italian UNI 9177 Classe Uno](#)

[Loci Dim Out American CAL 19](#)

[Loci Dim Out American Hospital washing standard AATCC96](#)

[Loci Dim Out American Boston BFD IX1](#)

[Loci Dim Out French NF P 92 503 507 M1](#)

[Loci Dim Out European EN 13773](#)

[Loci Dim out BS 5867 Part 2 Type B 2008](#)

[Loci Dim Out BS 5867 Part 2 Type C 2008 Master](#)

[Loci Dim Out American New York Port Authority FAR Part 25 853 12](#)

[Second Vertical Test](#)

[Loci Dim Out German DIN 4102 B1](#)

[Loci Dim Out Canadian CANULCS109](#)

[Loci Dim Out acoustic absorption draped](#)

[Loci Dim Out Swiss SNV 198898](#)

[Loci Dim Out American FMVSS 302](#)

[Loci Dim Out American NFPA 701](#)

