

COLLECTION: JUBILEA

DESIGN: JABBERWOCKY

BASIC INFORMATION

Brand	FR-One	Number of colour ways	5
Tariff item number	5407930000	MID	TRTEXTRABUR
Country of origin	Türkiye	Characteristics	Sheer
Vertical repeat cm	Stripe	Vertical repeat inch	Stripe
Horizontal repeat cm	7.00	Horizontal repeat inch	2.76
Double folded face in	Yes	Full roll diameter cm	31
Full roll diameter inch	12.2	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4
Railroaded	Yes		

CARE AND USAGE

Care code for washing °F Washable at 105°F gentle cycle

Care codes



Care code for bleaching Do not bleach

Use codes

Curtains Yes Curtains and draperies Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free Yes

COLLECTION: JUBILEA

DESIGN: JABBERWOCKY

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
American BFD IX 1	Yes	American CAL 19 section 1237.1	Yes
Canadian ULC S109 large flame	Yes	Canadian ULC S109 small flame	Yes
German B1 DIN 4102	Yes	European EN 13773	Yes
MVSS 302	Yes	IMO FTPC part 7 drapery	Yes
Japanese L 1091	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 701 2010	Yes	NYNJ Port Authority - FAR 25.853 12 Pass	Yes
SN 198'898 Class 5.2	Yes	Italian UNI 9174 Classe Uno	Yes

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	4.33
Construction	4x3.15	Woven	Yes
Useable width cm	300	Useable width inch	118.11
Full width cm	302	Full width inch	118.9
Weight g/m ²	165	Thickness mm	0.832
Colouring type	Yarn dyed	Filament or staple	54.25% Filament, 45.75% Staple
Textured or non textured	54.25% Textured, 45.75% Not Textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: JUBILEA

DESIGN: JABBERWOCKY

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	6
Acoustic absorption ISO 354 - ISO 11654	draped E/flat NA		

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Elongation - ISO 13934-1

Elongation warp %	24	Elongation weft %	26.5
-------------------	----	-------------------	------

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.48	Dimensional change weft	0.00
Dimensional change warp after ironing without steam	0.07	Dimensional change weft after ironing without steam	0.13
Dimensional change warp after ironing with steam	-0.13	Dimensional change weft after ironing with steam	0.60

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-2.48	Dimensional change warp after ironing	-2.38
Dimensional change weft	-3.45	Dimensional change weft after ironing	-3.92
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.91	Dimensional change warp after ironing	-2.92
Dimensional change weft	-3.27	Dimensional change weft after ironing	-3.77
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-3.54	Dimensional change warp after ironing	-3.79
Dimensional change weft	-3.26	Dimensional change weft after ironing	-3.79
Colour fastness ISO 105 D01	5		

COLLECTION: JUBILEA

DESIGN: JABBERWOCKY

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Is Textured	Yes	Warp Sizes	2090 den
Warp Textured	Yes	Warp Threads per cm	4
Warp TPM	NA		

Yarn 2

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	2090d	Warp Textured	Yes
Warp Threads per cm	1.94	Warp TPM	NA

Yarn 3

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2090d
Weft Threads per cm	1.67	Weft TPM	NA

Yarn 4

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	450 den	Weft Textured	Yes
Weft Threads per cm	0.86	Weft TPM	NA

DOWNLOADS / CERTIFICATES

- | | |
|---|---|
| Jabberwocky_American NFPA 701
Jabberwocky_French NF P 92 503507 M1
Jabberwocky_British BS 5867 part 2 type C
Jabberwocky_AustralianNew Zealand AS 1530 part 3
Jabberwocky_European EN 13773
Jabberwocky_International Maritime Organisation 2010 FTP Code Fire test procedures Part 7
Jabberwocky_American New York Port Authority FAR Part 25853 12 Second Vertical Test
Jabberwocky_German DIN 4102 B1 | JabberwockyItalian UNI 9177 Classe Uno
FROne_Sound absorption page
Jabberwocky_American Boston BFD IX1
Jabberwocky_British BS 5867 part 2 type B
Jabberwocky_American FMVSS 302

Jabberwocky_Swiss SNV 198898

Jabberwocky_AustralianNew Zealand AS 1530 part 2 |
|---|---|



