

COLLECTION: JUBILEA

DESIGN: JAIPUR

BASIC INFORMATION

Brand	FR-One	Number of colour ways	3
Tariff item number	5512199000	MID	TRTEXTRABUR
Country of origin	Türkiye	Characteristics	Sheer
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Double folded face in	Yes	Full roll diameter cm	24
Full roll diameter inch	9.45	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4
Railroaded	Yes		

CARE AND USAGE

Care code for washing °F

Washable at 105°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Accessories	Yes	Maritime	Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free

Yes

COLLECTION: JUBILEA

DESIGN: JAIPUR

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	Japanese L 1091	Yes
French NF P 92-503 507	M1	French NF P 92-504 507	M1
French NF P 92-505 507	M1	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Italian UNI 9174 Classe Uno	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	9.41
Construction	8x8	Woven	Yes
Useable width cm	300	Useable width inch	118.11
Full width cm	302	Full width inch	118.9
Weight g/m ²	170	Thickness mm	0.418
Colouring type	Yarn dyed	Filament or staple	100% staple
Textured or non textured	100% Not textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: JUBILEA

DESIGN: JAIPUR

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	6
Acoustic absorption ISO 354 - ISO 11654	draped E/flat NA		

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Elongation - ISO 13934-1

Elongation warp %	15	Elongation weft %	19.5
-------------------	----	-------------------	------

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.21	Dimensional change weft	-0.22
Dimensional change warp after ironing without steam	0.13	Dimensional change weft after ironing without steam	0.13
Dimensional change warp after ironing with steam	-0.47	Dimensional change weft after ironing with steam	0.53

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-0.80	Dimensional change warp after ironing	-0.86
Dimensional change weft	-0.93	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.96	Dimensional change warp after ironing	-1.73
Dimensional change weft	-1.06	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.52	Dimensional change warp after ironing	-0.73
Dimensional change weft	-1.03	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 D01	5		

COLLECTION: JUBILEA

DESIGN: JAIPUR

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	Ne 6/1
Warp Threads per cm	8	Warp TPM	NA

Yarn 2

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	Ne 6/1
Weft Threads per cm	8	Weft TPM	NA

DOWNLOADS / CERTIFICATES

Jaipur_American New York Port Authority FAR Part 25853 12 Second Vertical Test	Jaipur_Swiss SNV 198898
FROne_Sound absorption page	Jaipur_French NF P 92 503507 M1
Jaipur_American Boston BFD IX1	Jaipur_British BS 5867 part 2 type C
Jaipur_International Maritime Organisation 2010 FTP Code Fire test procedures Part 7	Jaipur_American Hospital washing standard AATCC96
Jaipur_British BS 5867 part 2 type B	Jaipur_AustralianNew Zealand AS 1530 part 2
Jaipur_American FMVSS 302	JaipurItalian UNI 9177 Classe Uno
Jaipur_German DIN 4102 B1	Jaipur_American NFPA 701
Jaipur_AustralianNew Zealand AS 1530 part 3	Jaipur_European EN 13773

