

COLLECTION: JUBILEA

DESIGN: JEDI

BASIC INFORMATION

Brand	FR-One	Number of colour ways	3
Tariff item number	5801370000	MID	TRTEKTEK4IST
Country of origin	Türkiye	Characteristics	Velvet
Vertical repeat cm	64.00	Vertical repeat inch	25.20
Horizontal repeat cm	70.00	Horizontal repeat inch	27.56
Face in	Yes	Full roll diameter cm	23
Full roll diameter inch	9.06	Average piece length m	40
Minimum for special colour m	600	Delivery time weeks special lab dip	2

CARE AND USAGE

Care code for washing °F	Washable at 140°F gentle cycle	Type of finish	brushed + dried
--------------------------	--------------------------------	----------------	-----------------

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes	Maritime	Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free

Yes

COLLECTION: JUBILEA

DESIGN: JEDI

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
British BS 5852 source 0	Yes	British BS 5852 source 1	Yes
British BS 5852 source 1 note	Yes, with FR coating	American CAL 117	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	European EN 1021 part 1 and 2	Yes
MVSS 302	Yes	IMO FTPC part 8 upholstery	Yes
IMO FTPC part 7 drapery	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 260	Yes	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Italian UNI 9174 Classe Uno	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	14.52
Construction	44x23.5	Woven	Yes
Useable width cm	138	Useable width inch	54.33
Full width cm	140	Full width inch	55.1
Weight g/m ²	465	Thickness mm	0.000
Colouring type	Printed	Filament or staple	18% filament - 82% staple
Textured or non textured	100% textured	Finish type	brushed + dried

Treatment

No treatment	Yes
--------------	-----

Type of finish

Washed	Yes
--------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes	Pile	Yes
-------	-----	------	-----

COLLECTION: JUBILEA

DESIGN: JEDI

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Martindale rubs	40,000
Colour fastness to light	5	Wyzenbeek double rubs	40,000
Pilling	4-5	Brush pilling	4
Wyzenbeek cotton duck double rubs	40,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	31	Tearing strength weft N	39
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	840	Tensile strength weft N/5cm	760
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	22	Elongation weft %	20.5
-------------------	----	-------------------	------

Seam slippage - ISO 13936-2

Seam slippage warp mm	4	Seam slippage weft mm	3
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.00	Dimensional change weft	-0.08
Dimensional change warp after ironing without steam	0.07	Dimensional change weft after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.20	Dimensional change weft after ironing with steam	0.27

COLLECTION: JUBILEA

DESIGN: JEDI

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.23	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-0.30	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.33	Dimensional change weft after ironing	-0.27
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74° C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.20	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.07	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	300 den	Warp Textured	Yes
Warp Threads per cm	22	Warp TPM	NA

Yarn 2

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	300 den	Warp Textured	Yes
Warp Threads per cm	22	Warp TPM	NA

Yarn 3

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	NE 20/1
Weft Threads per cm	23.5	Weft TPM	NA

COLLECTION: JUBILEA

DESIGN: JEDI

DOWNLOADS / CERTIFICATES

- | | |
|--|--|
|  <u>Jedi_American NFPA 260 UFAC</u> |  <u>FROne_Sound absorption page</u> |
|  <u>Jedi_American FMVSS 302</u> |  <u>Jedi_American CAL 19</u> |
|  <u>Jedi_AustralianNew Zealand AS 1530 part 3</u> |  <u>Jedi_AustralianNew Zealand AS 1530 part 2</u> |
|  <u>Jedi_American NFPA 701</u> |  <u>Jedi_International Maritime Organisation 2010 FTP Code Fire test pro-</u> |
|  <u>JubileaPrintItalian UNI 9177 Classe Uno</u> |  <u>cedures Part 8</u> |
|  <u>Jedi_American New York Port Authority FAR Part 25853 12 Second Ver-</u> |  <u>Jedi_American Hospital washing standard AATCC96</u> |
|  <u>tical Test</u> |  <u>Jedi_French NF P 92 503-507 (M1)</u> |
|  <u>Jedi_European EN 1021</u> |  <u>Jedi_European EN 13773</u> |
|  <u>Jedi_American Boston BFD IX1</u> |  <u>Jedi_British BS 5867 part 2 type B</u> |
|  <u>Jedi_American CAL 117 SecE June 2013</u> |  <u>Jedi_International Maritime Organisation 2010 FTP Code Fire test pro-</u> |
|  <u>Jedi_Swiss SNV 198898</u> |  <u>cedures Part 7</u> |
|  <u>Jedi_German DIN 4102 B1</u> |  <u>Jedi_British BS 5867 part 2 type C</u> |

