

COLLECTION: DARKNESS

DESIGN: DARKNESS

BASIC INFORMATIONS

Brand	Bru	Number of colour ways	27
Tariff item number	5903909900	MID	CNSUZFUR88SUZ
Country of origin	China	Characteristics	Blackout
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	18
Full roll diameter inch	7.09	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	2
Suspended box	Yes		

CARE CODES



CARE AND USAGE

Care code comments

Drip dry

Use codes

Curtains	Yes	Curtains and draperies	Yes
Bed covering	Yes	Accessories	Yes

ENVIRONMENTAL STANDARDS



STANDARD
100
2111231
Centexbel



Labels

GRS post-consumer

Yes

COLLECTION: DARKNESS

DESIGN: DARKNESS

FR STANDARDS

ASNZS 1530.2 Pass	Yes	British BS 5867 part 2 type B	Yes
American CAL 117	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	American NFPA 260	Yes
American NFPA 701 2010	Yes		

FABRIC SPECIFICATIONS

Composition	57% Recycled Polyester, 43% Polyacrylic	Average yarn number	24.87
Composition fabric	100% Recycled Polyester	Composition coating	100% Acrylic
Construction	56x41	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m²	390	Thickness mm	0.700
Colouring type	Piece dyed	Filament or staple	100% filament
Textured or non textured	100% textured		

Treatment

Backing	Yes
---------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

There are no technical details for this section.

Weaving type

Plain	Yes
-------	-----

COLLECTION: DARKNESS

DESIGN: DARKNESS

MECHANICAL PERFORMANCE

Martindale rubs	42,500	Colour fastness to light	6
Wyzenbeek double rubs	63,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	63,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Acoustic absorption ISO 354 – ISO 11654	D	Wyzenbeek wire screen medium duty	Yes

Colour fastness to light – ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to weathering – ISO 105-B04:1994

There are no technical details for this section.

Colour fastness to water – ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub – ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub – ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength – ISO 13937-3

Tearing strength warp N	167	Tearing strength weft N	150
-------------------------	-----	-------------------------	-----

Tensile strength – ISO 13934-1

Tensile strength warp N/5cm	1300	Tensile strength weft N/5cm	1400
-----------------------------	------	-----------------------------	------

Elongation – ISO 13934-1

Elongation warp %	36.5	Elongation weft %	27
-------------------	------	-------------------	----

Seam slippage – ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) – ISO 3759

Dimensional change warp	-0.05	Dimensional change warp after ironing with steam	-0.53
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.07
Dimensional change weft after ironing with steam	-0.60	Dimensional change weft after ironing without steam	0.00

COLLECTION: DARKNESS

DESIGN: DARKNESS

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.30	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.33	Dimensional change weft after ironing	-0.27
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 40° C, indicated in % - ISO 6330

There are no technical details for this section.

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.16	Dimensional change warp after ironing	1.86
Dimensional change weft	-1.93	Dimensional change weft after ironing	-1.93
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74 C ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.86	Dimensional change warp after ironing	-1.00
Dimensional change weft	-0.83	Dimensional change weft after ironing	-1.00
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	No
Warp Sizes	300D	Warp Textured	Yes
Warp Threads per cm	56	Warp TPM	0

Yarn 2

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	No
Weft Sizes	300D	Weft Textured	Yes
Weft Threads per cm	41	Weft TPM	0

COLLECTION: DARKNESS

DESIGN: DARKNESS

DOWNLOADS

-  [Darkness-NFPA 260_UFAC-42556](#)
-  [Darkness - 202301306-IMO7](#)
-  [Darkness Fabric Cert Fire Retardant AS 1530.2](#)
-  [Darkness - NFPA701](#)
-  [Darkness-FMVSS302-42556](#)
-  [Darkness -B1 in English](#)
-  [Darkness - BS5867](#)
-  [Darkness - IMO7](#)
-  [Darkness-Cal TB 117-2013-42556](#)
-  [Darkness -B1 in German](#)

