

COLLECTION: JUBILEA

DESIGN: JABORINE

BASIC INFORMATION

Brand	FR-One	Number of colour ways	4
Tariff item number	5407930000	MID	TRTEXTRABUR
Country of origin	Türkiye	Characteristics	Jacquard
Vertical repeat cm	29.00	Vertical repeat inch	11.42
Horizontal repeat cm	29.00	Horizontal repeat inch	11.42
Face in	Yes	Full roll diameter cm	19
Full roll diameter inch	7.48	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care code for washing °F

Washable at 140°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains
Accessories

Yes
Yes

Curtains and draperies

Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free

Yes

COLLECTION: JUBILEA

DESIGN: JABORINE

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	Japanese L 1091	Yes
French NF P 92-503 507	M1	French NF P 92-504 507	M1
French NF P 92-505 507	M1	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Italian UNI 9174 Classe Uno	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	44.62
Construction	80x36	Woven	Yes
Useable width cm	145	Useable width inch	57.09
Full width cm	147	Full width inch	57.87
Weight g/m ²	260	Thickness mm	0.465
Colouring type	Yarn dyed	Filament or staple	58.6% Filament, 41.4% Staple
Textured or non textured	31.3% Textured, 68.7% Not textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Sanforized	Yes	Thermofixed	Yes
------------	-----	-------------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: JUBILEA

DESIGN: JABORINE

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	5
Pilling	4-5	Brush pilling	4-5
Acoustic absorption ISO 354 - ISO 11654	draped C/flat D		

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4
-------------------------	---

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	32	Elongation weft %	22
-------------------	----	-------------------	----

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.21	Dimensional change weft	-0.08
Dimensional change warp after ironing without steam	0.07	Dimensional change weft after ironing without steam	0.00
Dimensional change warp after ironing with steam	-0.13	Dimensional change weft after ironing with steam	0.20

COLLECTION: JUBILEA

DESIGN: JABORINE

WASHABILITY

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.16	Dimensional change warp after ironing	-2.00
Dimensional change weft	-0.33	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.19	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.23	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	300d
Weft Threads per cm	18	Weft TPM	100

Yarn 2

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	Ne 20/2
Weft Threads per cm	18	Weft TPM	450

Yarn 3

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	75d	Warp Textured	Yes
Warp Threads per cm	80	Warp TPM	550

COLLECTION: JUBILEA

DESIGN: JABORINE

DOWNLOADS / CERTIFICATES

- | | |
|---|---|
|  <u>Jaborine_American CAL 19</u> |  <u>Jaborine_American NFPA 701</u> |
|  <u>Jaborine_European EN 13773</u> |  <u>Jaborine_Swiss SNV 198898</u> |
|  <u>FROne_Sound absorption page</u> |  <u>Jaborine_American Hospital washing standard AATCC96</u> |
|  <u>Jaborine_French NF P 92 503507 M1</u> |  <u>JaborineItalian UNI 9177 Classe Uno</u> |
|  <u>Jaborine_AustralianNew Zealand AS 1530 part 2</u> |  <u>Jaborine_British BS 5867 part 2 type B</u> |
|  <u>Jaborine_German DIN 4102 B1</u> |  <u>Jaborine_British BS 5867 part 2 type C</u> |
|  <u>Jaborine_AustralianNew Zealand AS 1530 part 3</u> |  <u>Jaborine_American FMVSS 302</u> |
|  <u>Jaborine_American New York Port Authority FAR Part 25853 12 Second</u> |  <u>Jaborine_International Maritime Organisation 2010 FTP Code_Fire test</u> |
|  <u>Vertical Test</u> |  <u>procedures Part 7</u> |
|  <u>Jaborine_American Boston BFD IX1</u> | |

