

COLLECTION: JUBILEA

DESIGN: JAGER

BASIC INFORMATION

Brand	FR-One	Number of colour ways	4
Tariff item number	5515129000	MID	TRTEXTRABUR
Country of origin	Türkiye	Characteristics	Jacquard
Vertical repeat cm	32.00	Vertical repeat inch	12.60
Horizontal repeat cm	35.00	Horizontal repeat inch	13.78
Face in	Yes	Full roll diameter cm	19
Full roll diameter inch	7.48	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care code for washing °F

Washable at 140°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Accessories	Yes	Maritime	Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD

100

0611045
Centexbel

PFA-free

Yes

COLLECTION: JUBILEA

DESIGN: JAGER

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	Japanese L 1091	Yes
French NF P 92-503 507	M1	French NF P 92-504 507	M1
French NF P 92-505 507	M1	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Italian UNI 9174 Classe Uno	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	57.3
Construction	66x40	Woven	Yes
Useable width cm	142	Useable width inch	55.91
Full width cm	144	Full width inch	56.69
Weight g/m ²	185	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	30.8% Filament, 69.2% Staple
Textured or non textured	10% Textured, 90% Not Textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: JUBILEA

DESIGN: JAGER

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	6
Pilling	3	Brush pilling	3
Acoustic absorption ISO 354 - ISO 11654	draped C/flat D		

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	31	Elongation weft %	20.5
-------------------	----	-------------------	------

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.02	Dimensional change weft	-0.08
Dimensional change warp after ironing without steam	0.20	Dimensional change weft after ironing without steam	0.00
Dimensional change warp after ironing with steam	-0.13	Dimensional change weft after ironing with steam	0.00

COLLECTION: JUBILEA

DESIGN: JAGER

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-0.93	Dimensional change warp after ironing	-0.86
Dimensional change weft	-0.40	Dimensional change weft after ironing	-0.47
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-1.60	Dimensional change warp after ironing	-1.46
Dimensional change weft	-0.77	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74° C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.76	Dimensional change warp after ironing	-0.40
Dimensional change weft	-0.36	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 D01	5		

COLLECTION: JUBILEA

DESIGN: JAGER

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	300d
Weft Threads per cm	10	Weft TPM	100

Yarn 2

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	Ne 30/2
Weft Threads per cm	10	Weft TPM	600

Yarn 3

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	Ne 30/2
Weft Threads per cm	10	Weft TPM	600

Yarn 4

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	Ne 15/1
Weft Threads per cm	10	Weft TPM	650

Yarn 5

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	20d	Warp Textured	Yes
Warp Threads per cm	66	Warp TPM	NA

DOWNLOADS / CERTIFICATES

- | | |
|---|---|
|  Jager_British BS 5867 part 2 type C |  Jager_AustralianNew Zealand AS 1530 part 3 |
|  Jager_European EN 13773 |  Jager_American Hospital washing standard AATCC96 |
|  FROne_Sound absorption page |  Jager_American FMVSS 302 |
|  Jager_American New York Port Authority FAR Part 25853 12 Second | |
|  Vertical Test |  JagerItalian UNI 9177 Classe Uno |
| |  Jager_International Maritime Organisation 2010 FTP Code Fire test |
|  Jager_German DIN 4102 B1 |  procedures Part 7 |
|  Jager_American NFPA 701 |  Jager_Swiss SNV 198898 |
|  Jager_AustralianNew Zealand AS 1530 part 2 |  Jager_British BS 5867 part 2 type B |
|  Jager_French NF P 92 503507 M1 |  Jager_American Boston BFD IX1 |



COLLECTION: JUBILEA

DESIGN: JAGER