

COLLECTION: **ATEN DIM OUT**

DESIGN: **ADITYA**

BASIC INFORMATION

Brand	FR-One	Number of colour ways	11
Tariff item number	5407520000	MID	TWLIPEN162TAI
Country of origin	Taiwan	Characteristics	Dimout
Vertical repeat cm	Stripe	Vertical repeat inch	Stripe
Horizontal repeat cm	1.40	Horizontal repeat inch	0.55
Face in	Yes	Full roll diameter cm	24
Full roll diameter inch	9.45	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE AND USAGE

Care code for washing °F

Washable at 105°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Accessories	Yes	Maritime	Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD

100

0611045
Centexbel

PFA-free

Yes

COLLECTION: ATEN DIM OUT

DESIGN: ADITYA

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 701 2010	Yes	NYNJ Port Authority - FAR 25.853 12 Pass	Yes
SN 198'898 Class 5.2	Yes	Italian UNI 9174 Classe Uno	Yes

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	50
Construction	112x38	Woven	Yes
Useable width cm	150	Useable width inch	59.06
Full width cm	152	Full width inch	59.84
Weight g/m ²	300	Light transmission	92%
Thickness mm	0.000	Colouring type	Piece dyed
Filament or staple	100% Filament	Textured or non textured	100% Textured

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: **ATEN DIM OUT**

DESIGN: **ADITYA**

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	5
Pilling	4	Brush pilling	4-5
Acoustic absorption ISO 354 - ISO 11654	draped B / flat C		

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strength warp N	80	Tearing strength weft N	64
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	1500	Tensile strength weft N/5cm	1500
-----------------------------	------	-----------------------------	------

Elongation - ISO 13934-1

Elongation warp %	38.5	Elongation weft %	34
-------------------	------	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	3	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.29	Dimensional change weft	0.08
Dimensional change warp after ironing without steam	0.00	Dimensional change weft after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.20	Dimensional change weft after ironing with steam	0.00

COLLECTION: **ATEN DIM OUT**

DESIGN: **ADITYA**

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-1.33	Dimensional change warp after ironing	-1.40
Dimensional change weft	-0.17	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-2.00	Dimensional change warp after ironing	-0.46
Dimensional change weft	-0.40	Dimensional change weft after ironing	-0.46
Colour fastness ISO 105 D01	5		

COLLECTION: **ATEN DIM OUT**

DESIGN: **ADITYA**

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	150d	Warp Textured	Yes
Warp Threads per cm	56	Warp TPM	NA

Yarn 2

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	75d	Warp Textured	Yes
Warp Threads per cm	56	Warp TPM	NA

Yarn 3


Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	150d	Weft Textured	Yes
Weft Threads per cm	19	Weft TPM	NA

Yarn 4

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	300d	Weft Textured	Yes
Weft Threads per cm	19	Weft TPM	NA

DOWNLOADS / CERTIFICATES

Aditya_Italian UNI 9177 Classe Uno	Aditya_Taiwanese CNS 10285 L3196
Aditya_British BS 5867 part 2 type B	FROne_Sound absorption page
Aditya_Australian New Zealand AS 1530 part 2	Aditya_American New York Port Authority FAR Part 25_853 12 Second Vertical Test
Aditya_American NFPA 701	Aditya_French NF P 92 503_507_M1
Aditya_International Maritime Organisation 2010 FTP Code_Fire test procedures Part 7	Aditya_European EN 13773
Aditya_Swiss SNV 198898	Aditya_American FMVSS 302
Aditya_British BS 5867 part 2 type C	Aditya_American Hospital washing standard AATCC96
Aditya_American Boston BFD IX_1	Aditya_Australian New Zealand AS 1530 part 3
Aditya_Acoustic sound absorption measurement_flat	Aditya_American CAL 19
Aditya_German DIN 4102_B1	Aditya_Canadian CAN ULC S109
Aditya_Acoustic sound absorption measurement_draped	



COLLECTION: **ATEN DIM OUT**

DESIGN: **ADITYA**