

COLLECTION: RE-STORE

DESIGN: RE-JUVENATE

BASIC INFORMATION

Brand	FR-One	Number of colour ways	9
Tariff item number	5407720000	MID	TWLIPEN162TAI
Country of origin	Taiwan	Characteristics	Dimout
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Double folded face in	Yes	Full roll diameter cm	29
Full roll diameter inch	11.42	Average piece length m	25
Minimum for special colour m	1000	Delivery time weeks special lab dip	2
Railroaded	Yes		

CARE AND USAGE

Care code comments Iron with steam Care code for washing °F Washable at 140°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains Yes Curtains and draperies Yes
Maritime Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
2111231
Centexbel



GRS post-consumer
Prop 65

Yes
Yes

PFA-free

Yes

COLLECTION: RE-STORE

DESIGN: RE-JUVENATE

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 117	Yes	American CAL 19 section 1237.1	Yes
Canadian ULC S109 large flame	Yes	Canadian ULC S109 small flame	Yes
German B1 DIN 4102	Yes	European EN 13773	Yes
MVSS 302	Yes	IMO FTPC part 7 drapery	Yes
Japanese L 1091	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 260	Yes	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Taiwanese CNS10285-L31961	Yes	Italian UNI 9174 Classe Uno	Yes

FABRIC SPECIFICATIONS

Composition	60% Recycled Polyester, 40% Polyester	Average yarn number	54.07
Construction	112x36	Woven	Yes
Useable width cm	300	Useable width inch	118.11
Full width cm	302	Full width inch	118.9
Weight g/m ²	290	Light transmission	94%
Thickness mm	0.740	Colouring type	Piece dyed
Filament or staple	100% Filament	Textured or non textured	100% Textured

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: RE-STORE

DESIGN: RE-JUVENATE

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	5
Wyzenbeek double rubs	5,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs	6,000
Wyzenbeek cotton duck double rubs	5,000	Wyzenbeek cotton duck type unrated	Yes
Acoustic absorption ISO 354 - ISO 11654	C	Wyzenbeek wire screen light duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	4-5
--------------------------	-----

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.12	Dimensional change weft	0.21
Dimensional change warp after ironing without steam	0.07	Dimensional change weft after ironing without steam	0.53
Dimensional change warp after ironing with steam	-0.13	Dimensional change weft after ironing with steam	0.13

COLLECTION: RE-STORE

DESIGN: RE-JUVENATE

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-1.22	Dimensional change warp after ironing	-1.12
Dimensional change weft	-0.03	Dimensional change weft after ironing	-0.46
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.51	Dimensional change warp after ironing	-2.51
Dimensional change weft	-0.60	Dimensional change weft after ironing	-0.26
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.92	Dimensional change warp after ironing	-0.73
Dimensional change weft	-0.26	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 D01	5		

COLLECTION: RE-STORE

DESIGN: RE-JUVENATE

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	75D	Warp Textured	Yes
Warp Threads per cm	51.5	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester inherent	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	150D	Weft Textured	Yes
Weft Threads per cm	5.3	Weft TPM	0

Yarn 3

Warp Composition	100% Polyester inherent	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	150D+225D	Warp Textured	Yes
Warp Threads per cm	70	Warp TPM	0

Yarn 4

Weft Composition	100% Polyester inherent	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	300D+225D	Weft Textured	Yes
Weft Threads per cm	30	Weft TPM	0

DOWNLOADS / CERTIFICATES

FROne_Sound absorption page	RE-Juvenate_Canadian CANULC-S109
RE-Juvenate_American CAL 19	RE-Store_French NF P 92 503-507 (M1)
RE-Store_German DIN 4102 (B1)	RE-Juvenate_Italian UNI 9177 (Classe Uno)
RE-Juvenate_American NFPA 701	RE-Juvenate_American CAL 117 Sec.E, June 2013
RE-Juvenate_British BS 5867 part 2 type C	RE-Juvenate_American Boston BFD IX-1
RE-Store_Acoustic sound absorption measurement	RE-Juvenate_American Hospital washing standard AATCC96
RE-Juvenate_European EN 13773	RE-Juvenate_British BS 5867 part 2 type B
RE-Juvenate_American New York Port Authority FAR Part 25.853 12	RE-Juvenate_International Maritime Organisation 2010 FTP Code - Fire test procedures Part 7
Second Vertical Test	RE-Juvenate_American FMVSS 302
RE-Juvenate_Taiwanese CNS 10285 L3196	
RE-Juvenate_American NFPA 260 UFAC	



