

COLLECTION: JUBILEA

DESIGN: JERMIAN

BASIC INFORMATION

Brand	FR-One	Number of colour ways	4
Tariff item number	5407613000	MID	TRTEXTRABUR
Country of origin	Türkiye	Characteristics	Sheer
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Full width roll	Yes	Full roll diameter cm	Null
Full roll diameter inch	Null	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4
Railroaded	Yes		

CARE AND USAGE

Care code for washing °F

Washable at 105°F gentle cycle

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Maritime	Yes		

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



STANDARD
100
0611045
Centexbel

PFA-free

Yes

COLLECTION: JUBILEA

DESIGN: JERMIAN

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
American CAL 19 section 1237.1	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	Yes	MVSS 302	Yes
IMO FTPC part 7 drapery	Yes	Japanese L 1091	Yes
French NF P 92-503 507	M1	French NF P 92-504 507	M1
French NF P 92-505 507	M1	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Italian UNI 9174 Classe Uno	Yes		

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	22.07
Construction	20x12	Woven	Yes
Useable width cm	315	Useable width inch	124.02
Full width cm	317	Full width inch	124.8
Weight g/m ²	145	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	100% Filament
Textured or non textured	100% Not Textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Sanforized	Yes	Thermofixed	Yes
------------	-----	-------------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: JUBILEA

DESIGN: JERMIAN

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Colour fastness to light	6
Acoustic absorption ISO 354 - ISO 11654	draped E/flat NA		

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Elongation - ISO 13934-1

Elongation warp %	37	Elongation weft %	35.5
-------------------	----	-------------------	------

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.02	Dimensional change weft	0.14
Dimensional change warp after ironing without steam	0.20	Dimensional change weft after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.34	Dimensional change weft after ironing with steam	0.13

WASHABILITY

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-0.93	Dimensional change warp after ironing	-0.80
Dimensional change weft	-0.07	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	6		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.39	Dimensional change warp after ironing	-2.73
Dimensional change weft	-0.03	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.29	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.17	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 D01	4-5		

COLLECTION: JUBILEA

DESIGN: JERMIAN

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	78d
Warp Threads per cm	20	Warp TPM	NA

Yarn 2

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	1785d
Weft Threads per cm	6	Weft TPM	NA

Yarn 3

Weft Composition	100% Polyester inherent FR	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	85d
Weft Threads per cm	6	Weft TPM	NA

DOWNLOADS / CERTIFICATES

- | | |
|--|--|
|  <u>Jermian_European EN 13773</u> |  <u>Jermian_American NFPA 701</u> |
|  <u>FROne_Sound absorption page</u> |  <u>Jermian_American Hospital washing standard AATCC96</u> |
|  <u>JermianItalian UNI 9177 Classe Uno</u> |  <u>Jermian_German DIN 4102 B1</u> |
|  <u>Jermian_French NF P 92 503507 M1</u> |  <u>Jermian_AustralianNew Zealand AS 1530 part 3</u> |
|  <u>Jermian_American New York Port Authority FAR Part 25853 12 Second</u> | |
|  <u>Vertical Test</u> |  <u>Jermian_Swiss SNV 198898</u> |
|  <u>Jermian_American Boston BFD IX1</u> |  <u>Jermian_International Maritime Organisation 2010 FTP Code Fire test</u> |
|  <u>Jermian_British BS 5867 part 2 type B</u> |  <u>procedures Part 7</u> |
|  <u>Jermian_British BS 5867 part 2 type C</u> |  <u>Jermian_American FMVSS 302</u> |
| |  <u>Jermian_AustralianNew Zealand AS 1530 part 2</u> |

