

COLLECTION: **DUEDE**

DESIGN: **DUEDE**

BASIC INFORMATION

Number of colour ways	26	Tariff item number	5407520000
MID	INDDEEXP167MUM	Country of origin	India
Characteristics	Dimout	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	24	Full roll diameter inch	9.45
Average piece length m	30	Minimum for special colour m	1000
Delivery time weeks special lab dip	2	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Bed covering	Yes	Accessories	Yes

ENVIRONMENTAL STANDARDS



GRS post-consumer

Yes

Prop 65

Yes

COLLECTION: **DUEDE**

DESIGN: **DUEDE**

FR STANDARDS

ASNZS 1530.2 Pass	Yes	British BS 5867 part 2 type B	Yes
American CAL 117	Yes	Canadian ULC S109 large flame	Yes
Canadian ULC S109 small flame	Yes	German B1 DIN 4102	Yes
European EN 13773	No	MVSS 302	Yes
IMO FTPC part 7 drapery	No	French NF P 92-503 507	M4
French NF P 92-504 507	M3	French NF P 92-505 507	M1
American NFPA 701 2010	Yes		

FABRIC SPECIFICATIONS

Composition	100% Recycled Polyester	Average yarn number	51.07
Construction	106x37	Woven	Yes
Useable width cm	307	Useable width inch	120.87
Full width cm	309	Full width inch	121.65
Weight g/m ²	280	Thickness mm	0.880
Colouring type	Piece dyed	Filament or staple	100% filament
Textured or non textured	100% textured		

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

COLLECTION: DUEDE

DESIGN: DUEDE

MECHANICAL PERFORMANCE

Martindale rubs	25,000	Colour fastness to light	4
Wyzenbeek double rubs	24,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	15,000
Wyzenbeek cotton duck double rubs	24,000	Wyzenbeek cotton duck type general upholstery	Yes
Acoustic absorption ISO 354 - ISO 11654	C	Wyzenbeek wire screen medium duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	5
-------------------------	---

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	3
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	140	Tearing strength weft N	140
-------------------------	-----	-------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	2100	Tensile strength weft N/5cm	1700
-----------------------------	------	-----------------------------	------

Elongation - ISO 13934-1

Elongation warp %	40	Elongation weft %	31
-------------------	----	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	2	Seam slippage weft mm	2
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.17	Dimensional change weft	0.14
Dimensional change warp after ironing without steam	0.00	Dimensional change weft after ironing without steam	-0.07
Dimensional change warp after ironing with steam	-0.40	Dimensional change weft after ironing with steam	-0.07

COLLECTION: DUEDE

DESIGN: DUEDE

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.60	Dimensional change warp after ironing	-0.53
Dimensional change weft	-0.46	Dimensional change weft after ironing	0.20
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-2.18	Dimensional change warp after ironing	-3.11
Dimensional change weft	-1.85	Dimensional change weft after ironing	-0.79
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74° C, indicated in % - AATCC 96

Dimensional change warp	-5.90	Dimensional change weft	-1.60
Colour fastness ISO 105 C06	4		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.22	Dimensional change warp after ironing	-0.26
Dimensional change weft	-0.26	Dimensional change weft after ironing	-0.26
Colour fastness ISO 105 D01	4-5		

COLLECTION: **DUEDE**

DESIGN: **DUEDE**

CONSTRUCTION

Yarn 1

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	150D	Warp Textured	Yes
Warp Threads per cm	35.5	Warp TPM	0

Yarn 2

Warp Composition	100% Recycled Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	80/72 FD	Warp Textured	Yes
Warp Threads per cm	70.5	Warp TPM	0

Yarn 3

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	300/96 SD	Weft Textured	Yes
Weft Threads per cm	24	Weft TPM	0

Yarn 4

Weft Composition	100% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	150D	Weft Textured	Yes
Weft Threads per cm	13	Weft TPM	0

DOWNLOADS / CERTIFICATES

There are no technical details for this section.



