

COLLECTION: **REGAL VELVETS**

DESIGN: **REMAIN**

BASIC INFORMATION

Brand	FR-One	Number of colour ways	5
Tariff item number	5801370000	MID	TRTEKTEK4IST
Country of origin	Türkiye	Characteristics	Velvet
Vertical repeat cm	17.30	Vertical repeat inch	6.81
Horizontal repeat cm	17.50	Horizontal repeat inch	6.89
Face in	Yes	Full roll diameter cm	22
Full roll diameter inch	8.66	Average piece length m	30
Minimum for special colour m	300	Delivery time weeks special lab dip	2

CARE AND USAGE

Care code for washing °F

Washable at 160°F

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes	Maritime	Yes

ENVIRONMENTAL STANDARDS

ISO 14001

Environmental
Management



**STANDARD
100**

0611045
Centexbel

PFA-free

Yes

Prop 65

Yes

COLLECTION: **REGAL VELVETS**

DESIGN: **REMAIN**

FR STANDARDS

AATCC 96 Complies	Yes	ASNZS 1530.2 Pass	Yes
ASNZS 1530.3 Pass	Yes	British BS 5867 part 2 type B	Yes
British BS 5867 part 2 type C	Yes	American BFD IX 1	Yes
British BS 7176 and 5852 source 5	Yes	American CAL 117	Yes
Canadian ULC S109 large flame	Yes	Canadian ULC S109 small flame	Yes
German B1 DIN 4102	Yes	European EN 13773	Yes
European EN 1021 part 1 and 2	Yes	MVSS 302	Yes
IMO FTPC part 8 upholstery	Yes	IMO FTPC part 7 drapery	Yes
Japanese L 1091	Yes	French NF P 92-503 507	M1
French NF P 92-504 507	M1	French NF P 92-505 507	M1
American NFPA 260	Yes	American NFPA 701 2010	Yes
NYNJ Port Authority - FAR 25.853 12 Pass	Yes	SN 198'898 Class 5.2	Yes
Taiwanese CNS10285-L31961	Yes	Italian UNI 9174 Classe Uno	Yes

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	18.11
Construction	63x23	Woven	Yes
Useable width cm	140	Useable width inch	55.12
Full width cm	142	Full width inch	55.91
Weight g/m ²	475	Thickness mm	1.280
Colouring type	Piece dyed	Filament or staple	37% Filament, 63% Staple
Textured or non textured	37% Textured, 63% Not Textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Thermofixed	Yes
-------------	-----

Type of print or dye

Disperse	Yes
----------	-----

Weaving type

Jacquard	Yes
----------	-----

COLLECTION: REGAL VELVETS

DESIGN: REMAIN

MECHANICAL PERFORMANCE

AATCC 96 - 165°F / 74°C - Complies	Yes	Martindale rubs	70,000
Colour fastness to light	5-6	Wyzenbeek double rubs	65,000
Pilling	4-5	Brush pilling	4-5
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	65,000
Wyzenbeek cotton duck type general upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	5-6
--------------------------	-----

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp N	190	Tearing strength weft N	860
-------------------------	-----	-------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	680
-----------------------------	------	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	28	Elongation weft %	14
-------------------	----	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	3	Seam slippage weft mm	3
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.05	Dimensional change weft	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft after ironing without steam	0.00
Dimensional change warp after ironing with steam	-0.46	Dimensional change weft after ironing with steam	0.20

COLLECTION: REGAL VELVETS

DESIGN: REMAIN

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 40° C, indicated in % - ISO 6330

Dimensional change warp	-0.10	Dimensional change warp after ironing	0.07
Dimensional change weft	-0.03	Dimensional change weft after ironing	-0.73
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-0.66	Dimensional change warp after ironing	-0.66
Dimensional change weft	-0.76	Dimensional change weft after ironing	-0.60
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 74°C, indicated in % - AATCC 96

Dimensional change warp	0.00	Dimensional change weft	0.00
-------------------------	------	-------------------------	------

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.07	Dimensional change warp after ironing	-0.93
Dimensional change weft	-0.03	Dimensional change weft after ironing	-0.93
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester inherent FR	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	3000DNY	Warp Textured	Yes
Warp Threads per cm	42	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester inherent FR	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	NE 20/1
Weft Threads per cm	23	Weft TPM	0

Yarn 3

Pile Composition	100% Polyester inherent FR	Pile Is Not High Tenacity	Yes
Pile Is Staple	Yes	Pile Sizes	NE 20/2
Pile Threads per cm	21	Pile TPM	0

COLLECTION: **REGAL VELVETS**

DESIGN: **REMAIN**

DOWNLOADS / CERTIFICATES

- | | |
|--|--|
|  <u>Regal Velvets_Acoustic sound absorption measurement</u> |  <u>Remain_European EN 13773</u> |
|  <u>FROne_Sound absorption page</u> |  <u>Regal Velvets_British BS7176 - BS5852 crib 5</u> |
|  <u>Regal Velvets_French NF P 92 503-507 (M1)</u> |  <u>Regal Velvets_American CAL 19</u> |
|  <u>Regal Velvets_European EN 1021</u> |  <u>Regal Velvets_British BS7175 Section 3 Source 5</u> |
|  <u>Remain_American NFPA 701</u> |  <u>Regal Velvets_American Boston BFD IX-1</u> |
|  <u>Remain_International Maritime Organisation 2010 FTP Code - Fire test procedures Part 7</u> |  <u>Remain_British BS 5867 part 2 type B</u> |
|  <u>Regal Velvets_International Maritime Organisation 2010 FTP Code - Fire test procedures Part 8</u> |  <u>Regal Velvets_American NFPA 260 UFAC</u> |
|  <u>Remain_Italian UNI 9177 (Classe Uno)</u> |  <u>Regal Velvets_German DIN 4102 (B1)</u> |
|  <u>Regal Velvets_American CAL 117 Sec.E, June 2013</u> |  <u>Regal Velvets_American Hospital washing standard AATCC96</u> |
|  <u>Remain_British BS 5867 part 2 type C</u> |  <u>Regal Velvets_American FMVSS 302</u> |
|  <u>Regal Velvets_American NFPA 701</u> |  <u>Regal Velvets_International Maritime Organisation 2010 FTP Code - Fire test procedures Part 9</u> |
|  <u>Regal Velvets_American New York Port Authority FAR Part 25.853 12</u> | |
|  <u>Second Vertical Test</u> | |

